

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

EP 0 769 574 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:

23.04.1997 Bulletin 1997/17

(51) Int. Cl.⁶: **C23G 1/08**

(21) Application number: **96116476.1**

(22) Date of filing: **15.10.1996**

(84) Designated Contracting States:

BE DE ES FI FR GB IT SE

(30) Priority: **18.10.1995 IT MI952141**

(71) Applicant: **NOVAMAX ITB s.r.l.**
Milano (IT)

(72) Inventors:

- **Pedrazinni, Cesare**
20149 Milano (IT)
- **Giordani, Paolo**
26013 Crema (IT)

(74) Representative: **Gervasi, Gemma, Dr. et al**
NOTARBARTOLO & GERVASI Srl,
Corso di Porta Vittoria, 9
20122 Milano (IT)

(54) **Process for stainless steel pickling and passivation without using nitric acid**

(57) Process for stainless steel pickling consisting in placing the material to be treated in a bath kept at a temperature ranging from 30°C to 70°C and containing:

- a) HCl
- b) Fe³⁺
- c) HF
- d) emulsifiers, wetting agents, polishing agents, acid attack inhibitors;

the bath being fed continuously with:

- an air flow equal to at least 3 m³/h per m³ bath min. and an oxidizer quantity adjusted to the bath redox potential to be kept at 250 mV min.

EP 0 769 574 A1

Description

Technical field

As it is known when, during the manufacturing process, iron and steel industry products undergo hot-rolling or intermediates undergo heat treatment, such as for instance annealing, the material is coated with a thinner or thicker oxidation layer. In consideration of the final products having to exhibit a polished and glossy finish, the oxidation layer is to be removed entirely. This is done through the well-known pickling process generally using mineral inorganic acids, such as hydrochloric acid, sulphuric acid, nitric acid, and hydrofluoric acid, either individually or as mixtures.

According to the industrial processes currently applied, stainless steel pickling is normally almost exclusively based on the use of a nitric-hydrofluoric acid mixture, the respective acid concentrations depending on the type of plant, on the type of steel to be pickled, on the steel surface properties and on the shape of the manufacture to be treated. Although the process is undoubtedly economic and leads to excellent results, it involves extremely serious ecological problems hard to solve, brought about by the use of nitric acid. Actually, while on the one hand highly polluting nitrogen oxide vapours having general formula NO_x , aggressive toward metallic and non-metallic materials with which they come into contact, are vented to the atmosphere, on the other hand high nitrate concentrations are reached in wash water and spent baths, both types of pollutants requiring treatment prior to disposal. The removal of NO_x from air and of nitrates from baths involves huge plant operation problems and high operating costs, with no certainty about the obtainment of targets complying with the regulations in force. This means that the resulting industrial plant investment costs can be hardly borne in most cases.

A pickling method not requiring the use of nitric acid is therefore demanded by industry and various proposals in this sense have been made worldwide mainly in these last ten years.

Prior art

A critical examination both of patents covering methods alternative to the traditional stainless steel pickling process based on the use of $\text{HNO}_3 + \text{HF}$, no longer containing nitric acid, and of the main relating technical literature has demonstrated the following:

A) Japanese patents JP 55018552 published on 8th February, 1980 and JP 55050468 published on 12th April, 1980 provide for three steps:

- (1) initial descaling in sulphuric or hydrochloric acid,
- (2) immersion, in the former case, in a potassium permanganate and inorganic acids (non

HF) solution, in the latter case, in a ferric nitrate, ferric sulphate and peroxydisulphuric acid solution,

(3) pressure water or ultrasonic final washing.

B) Swedish patent SE 8001911 published on 12th October, 1981 relates to a treatment in a sulphuric acid and hydrogen peroxide solution; treatment time range: from 1 to 120 minutes (preferred range: 1-20'); temperature range: from 10°C to 90°C (preferred range: 30-60°C).

C) German patent DE 3937438 published on 30th August, 1990 mainly applies to the wire treatment industry and provides for the use of a hydrofluoric acid solution containing Fe^{3+} fed as additive in the form of fluoride complex. Then, the solution is fed with a gas and/or an oxygenated fluid means, subjected to electrolysis to obtain nascent oxygen capable of oxidizing iron from bivalent to trivalent.

D) TOKAI Denka Kogyo's English patent 2,000,196 provides for the use of a pickling bath consisting of ferric sulphate and hydrofluoric acid. Sulphuric acid and hydrogen peroxide are added continuously in a 1:1 molar ratio, for the purpose of keeping an adequate ferric ion concentration. The patent claims the pickling treatment control method by continuous checking of the redox potential to be kept at ≥ 300 mV by controlled $\text{H}_2\text{SO}_4 + \text{H}_2\text{O}_2$ feeding.

E) Two much alike European patents, EP 188975 and EP 236354 (WO 87/01739), the respective priority dates whereof are 22nd January, 1985 and 19th September, 1985, provide for the use of a pickling solution consisting of hydrofluoric acid (5-50 g/l) and trivalent ferric ion added as fluoridated complexes, continuously blown into with air or oxygen; treatment time range: 30" to 5'; temperature range: 10°C to 70°C; continuous checking is recommended for redox potential, which should be kept at -200 to +800 mV, in the case of the former patent, and at +100 to +300 mV, in the case of the latter patent; if the potential requires to be raised, an oxidizer such as potassium permanganate or hydrogen peroxide should be added. All pickling tests were conducted on sheets only.

Finally, there are two further patents regarding the possibility of avoiding or minimizing the formation of nitrogen oxides NO_x in baths using nitric acid, by the direct addition of suitable oxidizers to the pickling bath: the former, Japanese patent JP 58110682 dated 1st July, 1983, provides for the use of hydrogen peroxide; the latter, Swedish patent SE 8305648 dated 15th April, 1985 - priority date 14th October, 1983, SE 835648 - provides for the use of hydrogen peroxide and/or, as an alternative, of urea.

Nevertheless, despite this proliferation of patents, the traditional process based on the use of nitric and hydrofluoric acid is still massively applied all over the world and none of the alternatives proposed thus far

and outlined above is being applied in industry.

A remarkable advance has been made with the pickling process disclosed in Applicant's European patent 582,121, which provides for the use of a $\text{H}_2\text{SO}_4 + \text{HF}$ bath containing Fe^{3+} and Fe^{2+} ions and operating at controlled redox potential. The reoxidation of Fe^{2+} ion to ferric ions is obtained by periodical additions of H_2O_2 to the pickling solution.

Summary of the invention

The process which is the subject of the present patent application is a technically valid and, in many respects, economic alternative to the aforementioned procedures. In particular, it is a valuable integration of Applicant's patent EP 582,121.

The process is based on the use of a pickling bath containing iron ions, HF, HCl and conventional additives, such as wetting agents, emulsifiers, polishing agents, inhibitors of acid attack, continuously or periodically fed with an oxidizing agent capable of converting the Fe^{2+} that forms during pickling to Fe^{3+} , while the pickling solution redox potential is maintained at the preset value. The oxidizing agent may be selected among the following classes of compounds:

- a) peroxidized acids, such as persulphuric acid and salts thereof;
- b) oxidized chlorine acids: chlorous and chloric acids as alkaline salts thereof, such as NaClO_2 , NaClO_3 ;
- c) soluble permanganates.

All aforesaid oxidizing agents may be fed to the bath as are or as an aqueous solution.

Detailed description of the invention

The operating temperature normally ranges from 30°C to 70°C , its value depending to a large extent on the type of steel and on the type of plant, in which connection it is of basic importance that the possibility of performing mechanical descaling upstream of chemical pickling be secured. The basic process features are described hereinafter.

It is very important to agitate the pickling bath continuously to renew the pickling solution in contact with the metal surface to be treated. A very effective method consists in the continuous blowing of a strong air flow into the bath.

Content of inorganic mineral acids in the bath

Several are the functions of hydrofluoric and hydrochloric acids: among the most important, those of maintaining process pH below 2.5 and of removing the oxides due to heat treatment from the steel surface. Hydrofluoric acid is meant to complex Fe^{3+} and Cr^{3+} ions as much as possible and to depassivate the oxi-

dized material, bringing the electrode potential to an active and/or active/passive dissolution area (see hereinafter). In the absence of hydrofluoric acid, the operating potential rises to the material steady passivity field and descaling practically does not take place. Hydrochloric acid contributes to the total and free acidity of the solution and to the dissolution of the oxidation layers. Since, in the course of pickling, the contents of the two acids, mainly of hydrofluoric acid, tend to reduce, periodical feeding of same has to be performed as a function of the results of bath analysis (determination of free acidity and fluoride ions). The acids concentration under normal operating conditions varies, depending on the treated material, from 5 to 50 g/l for hydrofluoric acid and from 20 to 100 g/l for hydrochloric acid. The pH of a pickling solution as it is (without dilution), measured by neutral pH Crison 2002 with ingold electrode, at room temperature is generally lower than 2.5.

Fe^{3+} ion content in the bath: the pickling solution contains an amount of Fe^{3+} ions not below 15 g/l and preferably equal at least to 30 g/l, initially added as ferric chloride or sulphate: the function of such ion is of replacing - as oxidizer - nitric acid, according to the reaction



favoured by the bath pH conditions.

During the process, proper conditions must continuously be secured to allow the iron dissolved in the bath to be partially present as Fe^{3+} .

The oxidation of Fe^{2+} to Fe^{3+} ions during the process to keep the latter concentration above the minimum preset value is secured by continuous oxidizer feeding, adjusted to the redox potential value, which is measured either constantly or periodically. The pickling bath is generally prepared with an initial oxidizer quantity to secure, also in the process start-up phase, an adequate redox potential value, adjusted to the type of steel to be pickled, to the surface properties of the manufacture (or semimanufactured product), as well as to the quantity and quality of hot-rolling or annealing scales.

The addition of oxidizer during the process is substantially adjusted to the preset bath oxidation potential, which is thus kept at the preset value. Pickling processes of stainless steel often imply the final passivation of the pickled material. Said treatment may be carried out in a bath of composition similar to the pickling bath composition, but with redox potential adjusted to higher values and with HCl replaced by H_3PO_4 . The baths using the oxidizers of class a) and class c) best suit said procedure.

Continuous air blowing

During pickling, a continuous air flow is kept in the bath, in the order of at least $3 \text{ m}^3/\text{m}^3$ bath per pickling hour. The air flow, admitted at a proper and constant rate, favours bath agitation, a major condition for good

pickling. Actually, agitation continuously perturbs the liminal layer of the bath, near the surface to be treated, which is thus continuously kept in direct contact with an ever renewed pickling solution. Air blowing into from the vessel bottom, through drilled pipes or proper blowing items, secures excellent mechanical agitation and pickling liquid homogenization.

Instead of air blowing, other means may be conveniently used to favour pickling bath agitation and secure a perfect homogenization of same and a continuous renewal of the solution in contact with the metal surface to be pickled, i.e. means setting the liquid bath in quick motion (supersounds, liquid forced-circulation) or conveying the liquid as jets or sprays to the surface to be treated.

Redox potential control: as is known, stainless steel behaviour in acid mixtures is characterized by polarization curves, which exhibit activity, passivity and transpassivity phases depending on the redox potential value (see Fig. 1).

Legend of Figure 1

EO_2EH_2	equilibrium potentials of O and H development reactions
E_p	critical passivation potential
E_{pc}	complete passivation potential
E_o	free corrosion or null (external) current potential
E_M	equilibrium potential of alloy anodic dissolution reaction
E_T	transpassivation potential

Legend of Figure 2

Chromium content influence on polarization curve: current density (abscissa) versus the critical passivation potential (ordinate).

- a) sufficient Cr
- b) less than sufficient Cr
- c) completely insufficient Cr

Legend of Figure 3

Polarization curve of oxidized Cr steel

- a) basic alloy peak
- b) dechromized alloy peak

Brief description of the figures

The typical curve of Fig. 1 applies, however, to steel of uniform composition and, mainly, with a chromium content sufficient to bring about passivability ($\text{Cr} > 12\%$). A lower chromium content modifies the polarization curve as shown by Fig. 2, namely it reduces the passivity field, while increasing the passivity current density and raising the critical passivation potential.

Since, under the scale formed by the hot-rolling or annealing oxide layer, a stainless steel type, such as the one which the pickling method of the invention refers to, always exhibits a thinner or thicker layer of dechromized alloy, i.e. poorer in chromium than its basic composition, the steel polarization curve always shows the trend indicated in Fig. 3, where the dechromized alloy peak is more or less clearly evident.

To make sure that descaling proper and a thorough removal of the dechromized alloy take place during pickling, with the restoration of max. surface passivability, the bath has to be placed under potentiostatic control conditions. This means that the operating redox potential has to be adjusted so that during the very pickling step it may remain in the range where the dechromized alloy anodic dissolution rate is the highest when compared with that of the basic alloy (hatched area, Fig. 3). It is possible to preset the said range as a function of the steel type, while guaranteeing basic metallic material passivation, after dechromized alloy removal.

During pickling, as the bivalent iron ion concentration in the bath rises, the bath redox potential tends to lower, but the addition of oxidizer allows to maintain said potential at optimal values, normally higher than 300 mV. In the applied processes the value of 700 mV is never exceeded.

Wishing to obtain material pickling and subsequent passivation in the same bath, the redox potential is to be kept at 350 mV min.

In case of any particular upstream steel treatment and if a subsequent passivation stage in a separate bath is envisaged, the pickling bath potential may be kept at lower values, anyway not below 200 mV.

The pickling solution redox potential is measured with a platinum electrode and a reference electrode, e.g. calomel or Ag/AgCl type.

A constant potential control, therefore, secures not only good steel pickling, but also an excellent subsequent passivation of pickled steel. Commercial-scale tests have, in fact, demonstrated the possibility of obtaining polished, bright, and perfectly even surfaces, free from any corrosion phenomenon due, for instance, to pitting, material "burning" or an excessive pickling action.

Additives content in the pickling bath

When preparing the pickling bath according to the present invention, the normal additives used, in a total amount of approx. 1 g/l bath, are non-ionic surfactants acting as wetting agents, emulsifiers, polishing agents, and acid attack inhibitors. Thanks to a synergic action, these additives improve pickling by favouring it.

Particularly advantageous additives are perfluorinated anionic surfactants as well as non-ionic surfactants belonging to the alkoxylated alcohol derivatives.

An efficient inhibitor guarantees basic metal protection, reduces losses drastically, and results highly effective.

tive mainly in the case of batch processes requiring long pickling time (rods, pipes, bars).

The additives present in the bath, particularly acid attack inhibitors, do not inhibit the attack against oxides caused by heat treatment, hence they do not absolutely limit pickling kinetics, as shown e.g. by the results of tests conducted on AISI 304 shot-peened sheet steel.

Advantages of the process

Absence of mud: the process according to the invention minimizes or even prevents the formation of mud and sludge, with a consequent clearcut further saving.

Such an advantage is also due to an appropriate HCl concentration during the process cycle, as well as to a control of the concentration of ferrous ions, readily and suitably oxidized to ferric ions.

Differently from the mud and sludge produced by traditional baths using nitric and hydrofluoric acids, the mud and sludge produced to a greatly smaller extent by the process bath of the invention are a greenish slush, friable and incoherent in the dry state, with no tendency to packing and lumping into large crystals and therefore easy to remove.

Automatic control possibility: the process according to the invention can always be kept under control by automatic means, which - through analytical determinations (free acids content, iron ion content, redox potential) - continuously meter the amounts of pickling materials and of oxidizer necessary to secure correct operating parameters.

Process versatility: the process according to the invention suits any existing commercial plant handling stainless steel as the required adjustments are quite modest. Furthermore, it is appropriate for the treatment of manufactures and semimanufactured products of any type whatever, from wire to rod, from belts to sheets and pipes, thanks to operating parameters (temperature, times, concentrations) being changeable to no detriment of results.

A typical example of such a versatility is represented by the possibility of combining pickling according to the invention with a passivation treatment, which, as mentioned above, is preferably carried out in a separate bath.

The following examples are being conveyed for the sole purpose of illustrating the possible applications of the process according to the invention.

Example 1

Continuous sheets from cold-rolling plants, i.e. sheets of steel series 300 and series 400, were treated according to a pickling procedure consisting of the following steps:

a) electrolytic pickling with H_2SO_4 in the 1st vessel; treatment time 1'; temperature range from 60°C to

70°C;

b) pickling with a bath according to the invention in the 2nd vessel; treatment time 2'; the pickling solutions composition and characteristics are shown in the Tables reported hereinafter.

The working capacity of the 2nd vessel is 17 m³.

During treatment, air is forced continuously into the vessel, at a rate of 10 m³/m³/h, along with a continuous feeding of oxidizer consisting of H₂O₂ as an aqueous solution at 35% by wt. and of the other ingredients (HF and HCl), so as to keep concentrations and redox potential at the preset values.

Table a'

Austenitic steel, series 300 - shot-peened	
	2nd vessel
Temperature, °C	35-65
HCl, g/l	60-100
Fe ³⁺ , g/l	20-60
HF, g/l	20-30
E redox, mV	> 280

Table b'

Austenitic steel, series 300 - non-shot-peened	
	2nd vessel
Temperature, °C	35-65
HCl, g/l	60-100
Fe ³⁺ , g/l	20-60
HF, g/l	30-40
E redox, mV	> 280

Table c'

Austenitic steel, series 400 - shot-peened	
	2nd vessel
Temperature, °C	30-60
HCl, g/l	60-100
Fe ³⁺ , g/l	30-50
HF, g/l	10-20
E redox, mV	200-300

In all cases, the pickled material was subjected to passivation in the 3rd vessel containing:

HF, g/l	5
Fe ³⁺ , g/l	2
H ₃ PO ₄ , g/l	25
E redox, mV	500 approx.

The redox potential was kept at the preset value by periodical additions of H₂O₂. The bath temperature was 30° C max.; the treatment time was 90".

The superficial aspect of sheets at the end of the pickling process cycle always resulted to be polished and bright.

In this case too, no overpickling or superficial corrosion phenomenon was recorded.

Claims

1. Pickling process for chromium containing stainless steel comprising placing the material to be treated in a bath kept at a temperature ranging from 30°C to 70°C, preferably from 45°C to 55°C, having the following composition:

- a) HCl from 25 to 120 g/l
- b) Fe³⁺ at least 15 g/l, preferably at least 30 g/l
- c) HF from 5 to 50 g/l
- d) additives (emulsifiers, wetting agents, polishing agents) and acid attack inhibitors: approx. 1 g/l on the whole;

said bath, kept under agitation by a continuous air flow or equivalent agitation means, being fed continuously or periodically with: quantities of ingredients a), c), and d) securing optimal concentration levels in the bath and a bath pH equal to 2.5 max. and an oxidizer quantity suitable for keeping the bath redox potential at values of at least 200 mV, said oxidizing agent being selected among the following classes of compounds:

- a) H₂O₂, peroxidized acids, such as persulphuric acid and salts thereof;
- b) oxidized chlorine acids: chlorous and chloric acids as alkaline salts thereof, such as NaClO₂, NaClO₃;
- c) alkaline permanganates;

said oxidizing agents being fed to the bath as such or as an aqueous solution thereof.

2. The process according to claim 1, wherein the pickling bath is adjusted to an oxidation potential of 350 mV min., which secures appropriate pickled mate-

rial passivation.

3. The process according to claim 1, wherein the pickling bath is continuously fed with an air flow equal to at least 3 m³/h per m³ bath, through a diffuser distributing the flow in the liquid mass.

4. The process according to claim 1, wherein Fe³⁺ ions are introduced into the initial bath as ferric sulphate.

5. The process according to claim 1, wherein a surfactant belonging to the class of non-ionic surfactant alkoxyated alcohol derivatives containing 6 C atoms min. and of perfluorinated anionic surfactants, is used as wetting agent, emulsifier, polishing agent, and acid attack inhibitor.

6. The process according to claim 1, combined with a preliminary partial removal of oxides by a known mechanical method.




Fig.1 Typical polarization curve of stainless steel in deaerated acid solution




FIG. 2




FIG. 3

EP 0 769 574 A1

European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 96 11 6476

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
A	PATENT ABSTRACTS OF JAPAN vol. 010, no. 120 (C-343), 6 May 1986 & JP-A-60 243289 (KOBE SEIKOSHO KK), 3 December 1985, * abstract *	1	C23G1/08
D,A	EP-A-0 582 121 (ITB SRL) 9 February 1994 * claims 1-7 *	1	
A	CHEMICAL ABSTRACTS, vol. 54, no. 2, 25 January 1960 Columbus, Ohio, US; abstract no. 1245a, SUMITOMO: "Pickling of stainless steel, heat resistant steel, nickel and nickel alloys" page 1245; XP002005390 * abstract * & JP-A-34 002 577 (SUMITOMO)	1	
A	EP-A-0 626 469 (MANNESMANN AG) 30 November 1994 * claim 9 *	1	TECHNICAL FIELDS SEARCHED (Int.Cl.6) C23G
A	EP-A-0 188 975 (CHETREFF BERNARD) 30 July 1986	1	
A	FR-A-2 551 465 (FORGES DE GUEUGNON) 8 March 1985 * claims 1,11,12 *	1	
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 10 January 1997	Examiner Torfs, F
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application I : document cited for other reasons & : member of the same patent family, corresponding document	

EPO FORM 1501 (03.82) (P04C01)